

March, 2018

3M™ Scotch-Weld™ Low Odor Acrylic Adhesive DP8825NS Green

Product Description

3M™ Scotch-Weld™ Low Odor Acrylic Adhesives are high performance, two-part acrylic adhesives that offer excellent shear, peel, and impact performance. These toughened products provide improved adhesion to many plastics and metals, including those with slightly oily surfaces. These durable products feature a fast rate of strength build, providing structural strength in minutes. Their low odor and non-flammability features also make them easier to incorporate into a manufacturing process.

Review UL File QOQW2. MH17478 and Sign Components Manual (SAM) File E464624 for certification of these adhesive systems in electrical equipment.

Product Features

- Toughened
- Excellent shear strength
- High peel and impact strength
- 10:1 mix ratio control bond line thickness
- Variety of open times available
- Increased cure speed with applied heat
- Contain glass beads (0.010" diameter) to control bond line thickness

Note: Unless otherwise indicated, all properties measured at 72°F (22°C).



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Property	Values	Notes
Base Color	Off-White	
Accelerator Color	Blue	
Base Density	1.12 g/cm ³	Density measured using pycnometer.
Accelerator Density	1.08 g/cm ³	Density measured using pycnometer.
Base Viscosity	40000 cP	Viscosity measured using cone-and-plate viscometer; reported viscosity at 3.8 sec ⁻¹ shear rate.
Accelerator Viscosity	15000 cP	Viscosity measured using cone-and-plate viscometer; reported viscosity at 3.8 sec ⁻¹ shear rate.
Mix Ratio by Volume (B:A)	10:1	
Mix Ratio by Weight (B:A)	10:1	

Typical Performance Characteristics

Additional Test notes

Note: Environmental aging tests have shown that these adhesives may accelerate the corrosion of certain bare metals (such as cold rolled steel, copper, brass, and bronze), leading to low bond strength values and early bond failure. These adhesives also have relatively low adhesion to low surface energy plastics (such as polypropylene, polyethylene, TPO, and PTFE). Applications involving any of these materials should be carefully evaluated by the end user for suitability.

Note: The presence of oxygen inhibits the cure of acrylic structural adhesives. Therefore, any exposed surfaces of the mixed adhesive will cure much more slowly than adhesive contained within the bond line. With methyl methacrylate (MMA) acrylic adhesives, any uncured adhesive on the surface flashes off immediately, leaving a surface that feels dry to the touch. With these low odor acrylic adhesives, uncured adhesive on exposed surfaces does not evaporate away quickly, leaving a wet film of partially cured material. For manufacturing processes that need a dry surface quickly, such as for subsequent sanding or painting operations, consider instead the standard acrylic adhesives (DP8405NS Green, DP8410NS Green, DP8425NS Green, and Metal Bonder DP8407NS Green).

Typical Performance Characteristics (continued)

Bell Peel: 30 lb/in width

Conditions

Dwell/Cure Time: 24 hr @ Room Temperature

Substrate: Aluminum

Failure mode: CF

Methods

ASTM D3167

Additional Information

Notes: 1" wide samples; 0.017" bond line thickness; samples pulled at 6 in/min; aluminum surfaces etched; substrates used were 1/16" thick and 0.020" thick aluminum.

Note: The data in this sheet were generated using the 3M™ EPX™ Applicator System equipped with an EPX static mixer, according to manufacturer's directions. Thorough hand-mixing will afford comparable results.

Cohesive Failure (CF), Adhesive Failure (AF), Substrate Failure (SF)

Environmental Resistance	Temp C	Temp F	Environmental Condition	Substrate
35 %	49C	120F	Water	Aluminum
45 %	32C	90F	Water	Aluminum
70 %	66C	150F	80%RH	Aluminum
95 %	-40C	-40F		Aluminum
100 %	149C	300F		Aluminum
75 %	49C	120F	80%RH	Aluminum
30 %	85C	185F	85%RH	Aluminum
60 %	22C	72F	Water	Aluminum
75 %	22C	72F	Salt water (5 wt% in water)	Aluminum
95 %	22C	72F	Diesel Fuel	Aluminum
100 %	22C	72F	Motor Oil	Aluminum
95 %	22C	72F	Antifreeze (50 wt% in water)	Aluminum
65 %	22C	72F	Isopropyl Alcohol (IPA)	Aluminum
75 %	22C	72F	Bleach (10 wt% in water)	Aluminum
85 %	-40C	-40F		Polyvinyl chloride (PVC)
90 %	49C	120F		Polyvinyl chloride (PVC)
90 %	66C	150F		Polyvinyl chloride (PVC)
100 %	22C	72F	Water	Polyvinyl chloride (PVC)
100 %	22C	72F	Salt water (5 wt% in water)	Polyvinyl chloride (PVC)
100 %	22C	72F	Hydrochloric acid (16 wt% in water)	Polyvinyl chloride (PVC)

Table continued on next page

Typical Performance Characteristics (continued)

Environmental Resistance	Temp C	Temp F	Environmental Condition	Substrate
65 %	22C	72F	Sodium hydroxide (10 wt% in water)	Polyvinyl chloride (PVC)
85 %	85C	185F	85%RH	Polyvinyl chloride (PVC)

Property: Environmental Resistance

Method: ASTM D1002

Attribute Modifier: Overlap Shear

Dwell/Cure Time: 1000

Dwell Time Units: hr

notes: Values indicate overlap shear test performance retained after 1,000 hours of continuous exposure relative to a control sample left at room temperature.

Samples exposed after 24hr dwell at Room temperature. Note: Fully-cured structural adhesives can withstand short-term incidental contact with almost any solvent, chemical, or environmental condition. However, long-term continuous exposure of these Low Odor Acrylic Adhesives to the following liquids should be avoided: 1. Elevated temperature (>100°F) water 2. Ketone-type solvents (acetone, MEK) 3. Gasoline and similar liquids

Typical Mixed Physical Properties

Property	Values	Test Condition	Notes
Color	Blue-Green	Mixed	
Viscosity	40000 cP		
Density (mixed)	1.12 g/cm ³		
Worklife	22 to 24 min	(Nozzle Mixed) @ Room Temperature	Maximum time that adhesive can remain in a static mixing nozzle and still be expelled without undue force on the applicator.
Open Time	20 to 22 min		Maximum time allowed after applying adhesive to one substrate before bond must be closed and fixed in place. Cure times are approximate and depend on adhesive temperature.
Time to Handling Strength	42 to 46 min	Room Temperature	Minimum time required to achieve 50 psi of overlap shear strength. Cure times are approximate and depend on adhesive temperature.
Time to Structural Strength	50 to 56 min		Minimum time required to achieve 1,000 psi of overlap shear strength. Cure times are approximate and depend on adhesive temperature.
Time to Full Cure	24 h	Room Temperature	

Typical Cured Characteristics

Property	Values	Method	Dwell/Cure Time	Notes
Modulus	Not Tested lb/in ²	ASTM D638	2 wk @ Room Temperature	1/8" thick Type I test specimens; samples pulled at 0.2 in/min.
Tensile Strength	Not Tested lb/in ²	ASTM D638	2 wk @ Room Temperature	1/8" thick Type I test specimens; samples pulled at 0.2 in/min.
Tensile Strain at Break	Not Tested %	ASTM D638	2 wk @ Room Temperature	1/8" thick Type I test specimens; samples pulled at 0.2 in/min.

Handling/Application Information**Directions for Use**

1. To obtain the highest strength structural bonds, paint, oxide films, oils, dust, mold release agents, and all other surface contaminants must be completely removed. The amount of surface preparation depends on the required bond strength and environmental aging resistance desired by user. For suggested surface preparations on common substrates, see the section on surface preparation.

2. Mixing For Duo-Pak Cartridges

Store cartridges with cap end up to allow any air bubbles to rise towards the tip. To use, simply insert the cartridge into the EPX applicator and start the plunger into the cylinders using light pressure on the trigger. Then remove the cap and expel a small amount of adhesive to ensure material flows freely from both sides of cartridge. For automatic mixing, attach an EPX mixing nozzle to the cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of adhesive and mix thoroughly. Mix approximately 15 seconds after obtaining a uniform color.

For Bulk Containers

Mix thoroughly by weight or volume in the proportion specified on the product label or in the typical uncured properties section. Mix approximately 15 seconds after obtaining a uniform color.

3. Apply adhesive and join surfaces within the open time listed for the specific product. Larger quantities and/or higher temperatures will reduce this working time.

4. Allow adhesive to cure at 60°F (16°C) or above until completely firm. Applying heat up to 150°F (66°C) will increase cure speed.

5. Keep parts from moving during cure. Apply contact pressure or fixture in place if necessary. Optimum bond line thickness ranges from 0.005 to 0.020 inch; shear strength will be maximized with thinner bond lines, while peel strength reaches a maximum with thicker bond lines.

6. Excess uncured adhesive can be cleaned up with ketone-type solvents.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Handling/Application Information (continued)

Surface Preparation

3M™ Scotch-Weld™ Low Odor Acrylic Adhesives are designed to be used on painted or coated metals, most plastics, glass, and some bare metals. The following cleaning methods are suggested for common surfaces:

Painted/coated metals:

1. Wipe surface free of dust and dirt with clean cloth and pure isopropyl alcohol.*
2. Sandblast or lightly abrade using clean fine grit abrasives. Do not completely remove the paint layer or coating down to bare steel.
3. Wipe again with clean cloth and pure isopropyl alcohol to remove loose particles.*

Aluminum/stainless steel:

1. Wipe surface free of dust and dirt with clean cloth and pure acetone.*
2. Sandblast or lightly abrade using clean fine grit abrasives.
3. Wipe again with clean cloth and pure acetone to remove loose particles.*

Plastics:

1. Wipe surface free of dust and dirt with clean cloth and pure isopropyl alcohol.*
2. Lightly abrade using fine grit abrasives.
3. Wipe again with clean cloth and pure isopropyl alcohol to remove loose particles.*

Glass:

1. Wipe surface free of dust and dirt with clean cloth and pure acetone.*
2. Apply a thin coating of silane adhesion promoter to the glass surface and allow to dry completely before adhesive bonding.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Storage and Shelf Life

Store product at 80°F (27°C) or below. Refrigeration at 40°F (4°C) will help extend shelf life. Do not freeze. Allow product to reach room temperature prior to use. 3M™ Scotch-Weld™ Low Odor Acrylic Adhesives have a shelf life of 24 months from date of manufacture in unopened original containers kept at recommended storage conditions.

Industry Specifications

Review UL File QOQW2. MH17478 and Sign Components Manual (SAM) File E464624 for certification of these adhesive systems in electrical equipment. EN 45545 test report for details (ISO 5659-2, ISO 9239-1, ISO 5660-1, ISO 5658-2)

Trademarks

3M, Scotch-Weld and EPX are trademarks of 3M Company.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~//3M-Scotch-Weld-Low-Odor-Acrylic-Adhesive-DP8825NS?N=5002385+3292929823&rt=rud
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=DP8825NS Green

3M™ Scotch-Weld™ Low Odor Acrylic Adhesive DP8825NS Green

Family Group

	DP8805NS Green	DP8810NS Green	DP8825NS Green
Worklife (min) Test Condition: (Nozzle Mixed) @ Room Temperature	3 to 5	8 to 12	22 to 24
Time to Full Cure (h) Test Condition: Room Temperature	24	24	24
Time to Handling Strength (min) Test Condition: Room Temperature	6 to 8	16 to 20	42 to 46
Color Test Condition: Mixed	Blue-Green	Blue-Green	Blue-Green
Open Time (min)	4 to 6	8 to 12	20 to 22
Time to Structural Strength (min)	8 to 10	19 to 23	50 to 56

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

