

# 3M

## Scotch-Weld™

### Epoxy Adhesives

#### DP-105 Clear

#### Technical Data

December, 2009

#### Product Description

3M™ Scotch-Weld™ Epoxy Adhesive DP-105 Clear is available in larger containers like 3M™ Scotch-Weld™ Epoxy Adhesive 105 B/A Clear.

Scotch-Weld DP-105 Clear is a fast setting, very flexible 1:1 mix ratio epoxy adhesive/sealant. Its flexibility when cured makes it ideal for applications involving dissimilar surfaces where thermal coefficient of expansion may be a problem. It is also unique in that it retains its clear, colorless properties even when cured in larger masses where many clear epoxy systems will often turn amber from the reaction exotherm.

#### Features

- 4 minute worklife
- Flexible
- Clear
- High peel strength
- 1:1 mix ratio

#### Typical Uncured Physical Properties

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

##### Footnotes:

1. Viscosity determined using 3M test method C-1d. Procedure involves Brookfield RVF, #7 spindle, 20 rpm and 80°F (27°C). Measurement taken after 1 minute rotation.
2. Worklife determined using 3M test method C-3180. Procedure involves periodically measuring a 2 gram mixed mass for self-leveling and wetting properties. This time will also approximate the usable worklife in an EPX mixing nozzle.

| Product                                            |                             | Scotch-Weld DP-105 Clear                |
|----------------------------------------------------|-----------------------------|-----------------------------------------|
| Base Resins                                        |                             | Epoxy/Mercaptan                         |
| Color                                              | Base (B)<br>Accelerator (A) | Clear<br>Clear                          |
| Net Weight (Lbs./Gallon)                           | Base (B)<br>Accelerator (A) | 9.1 - 9.5<br>9.4 - 9.8                  |
| Viscosity <sup>1</sup> , Approximate @ 80°F (27°C) | Base (B)<br>Accelerator (A) | 1,000 - 5,000 cps<br>8,000 - 16,000 cps |
| Mix Ratio (B:A)                                    | By Volume<br>By Weight      | 1:1<br>1:0.97                           |
| Worklife <sup>2</sup> @ 73°F (23°C)                | 2 gram<br>20 gram           | 5 minutes<br>4 minutes                  |

# 3M™ Scotch-Weld™

## Epoxy Adhesives

### DP-105 Clear

#### Typical Cured Properties

##### Footnotes:

2. Worklife determined using 3M test method C-3180. Procedure involves periodically measuring a 2 gram mixed mass for self-leveling and wetting properties. This time will also approximate the usable worklife in an EPX mixing nozzle.
3. Tack-free determined per 3M test method C-3173. Involves dispensing 0.5 gram amount of adhesive onto substrate and testing periodically for no adhesive transfer to metal spatula.
4. Handling strength determined per 3M test method C-3179. Time to handling strength taken to be that required to achieve a 50 psi OLS strength using aluminum substrates.
5. The cure time is defined as that time required for the adhesive to achieve a minimum of 80% of the ultimate strength as measured by aluminum-aluminum OLS.
6. Tensile and Elongation. Used procedure in 3M test method C-3094/ASTM D 882. Samples were 2" dumbbells with .0125" neck and .030" sample thickness. Separation rate was 2 inches per minute. Samples cured 2 hrs RT plus 2 hrs/160°F (71°C).
7. Weight loss by TGA reported as that temperature at which 5% weight loss occurs by TGA in air at 5°C (4°F) rise per minute per ASTM 1131-86.
8. TCE determined using Dupont TMA Analyzer using a heating rate of 50°F (10°C) per minute. Second heat values given.
9. Glass Transition Temperature (Tg) determined using Perkin Elmer DSC Analyzer with a heating rate of 68°F (20°C) per minute. Second heat values given.
10. Thermal conductivity determined using ASTM C177 and C-matic Instrument using 2 inch diameter samples.
11. Thermal shock resistance run per 3M test method C-3174. Involves potting a metal washer into a 2" x 0.5" thick section and cycling this test specimen to colder and colder temperatures.

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

|                                              | Scotch-Weld DP-105 Clear |
|----------------------------------------------|--------------------------|
| <b>Physical</b>                              |                          |
| <b>Color</b>                                 | Clear                    |
| <b>Hardness Shore D (ASTM D 2240)</b>        | 39                       |
| <b>Worklife<sup>2</sup></b>                  | 3-4 minutes              |
| <b>Tackfree Time<sup>3</sup></b>             | 10 minutes               |
| <b>Time to Handling Strength<sup>4</sup></b> | 20 min. @ 23°C (73°F)    |
| <b>Cure Time<sup>5</sup></b>                 | 48 hrs. @ 23°C (73°F)    |
| <b>Elongation<sup>6</sup></b>                | 120%                     |
| <b>Tensile Strength<sup>6</sup></b>          | 600 psi                  |

|                                                                                                                                                   |                                          |
|---------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------|
| <b>Thermal</b>                                                                                                                                    |                                          |
| <b>Weight Loss by Thermal Gravimetric Analysis (TGA)<sup>7</sup></b>                                                                              | 1% @ 117°C (243°F)<br>5% @ 289°C (552°F) |
| <b>Thermal Coefficient of Expansion (TCE) by TMA<sup>8</sup><br/>(<math>\infty \times 10^{-6}</math> units/unit/°C)<br/>Below Tg<br/>Above Tg</b> | —<br>181 (40-140°C range)                |
| <b>Glass Transition Temperature (Tg) by DSC<sup>9</sup><br/>Onset<br/>Mid-Point</b>                                                               | 8°C (46°F)<br>15°C (59°F)                |
| <b>Thermal Conductivity<sup>10</sup><br/>(@ 110°F on .250" samples)<br/>BTU-ft./ft.<sup>2</sup> - hr.-°F<br/>Cal./sec -cm-°C<br/>Watt/m-°C</b>    | .085<br>.35 x 10 <sup>-3</sup><br>.147   |
| <b>Thermal Shock Resistance<sup>11</sup><br/>Potted Washer Olyphant Test<br/>(3M/AdhD Test Method C-3174<br/>+100°C [air] to -50°C [liquid])</b>  | Pass 5 cycles<br>without cracking        |

|                                                                             |                               |
|-----------------------------------------------------------------------------|-------------------------------|
| <b>Electrical</b>                                                           |                               |
| <b>Dielectric Constant @ 1 KHz<br/>@ 23°C (73°F) [ASTM D 150]</b>           | 9.2                           |
| <b>Dissipation Factor @ 1 KHz<br/>@ 23°C (73°F) [ASTM D 150]</b>            | 0.22                          |
| <b>Dielectric Strength (ASTM D 149)<br/>Sample Thickness Approx. 30 mil</b> | 465 volts/mil                 |
| <b>Volume Resistivity (ASTM D 257)</b>                                      | 1.5 x 10 <sup>10</sup> ohm-cm |

# 3M™ Scotch-Weld™

## Epoxy Adhesives

### DP-105 Clear

#### Typical Adhesive Performance Characteristics

The following product performance data was obtained in the 3M laboratory under the conditions specified. The following data show typical results obtained with the 3M™ Scotch-Weld™ Adhesives when applied to properly prepared substrates, cured, and tested according to the specifications indicated. This data was generated using the 3M™ Scotch-Weld™ EPX™ Applicator System equipped with an EPX static mixer, according to manufacturer's directions. Thorough hand mixing should afford comparable results.

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

#### Footnotes:

12. Overlap shear (OLS) strengths were measured on 1" wide 1/2" overlap specimens. These bonds were made individually using 1" x 4" pieces of substrate. The thickness of the bond line was 0.005-0.008". All strengths were measured at 70°F (21°C) except where noted. (Test per ASTM D 1002-72.)

The separation rate of the testing jaws was 0.1" per minute for metals, 2" per minute for plastics and 20" per minute for rubbers. The thickness of the substrates were: steel, 0.060"; other metals, 0.05-0.064"; rubber, 0.125"; plastics, 0.125".

|                                                                                               | Scotch-Weld DP-105 Clear |
|-----------------------------------------------------------------------------------------------|--------------------------|
| <b>Overlap Shear (OLS) to<sup>12</sup></b><br>(Bonds aged 24 hrs @ RT + 2 hrs @ 160°F (71°C)) |                          |
| <b>Etched Aluminum</b>                                                                        | 2000 psi                 |
| <b>Sanded Aluminum (60 grit)</b>                                                              | 1500 psi                 |
| <b>Cold Rolled Steel</b>                                                                      | 1300 psi                 |
| <b>Wood, Fir</b>                                                                              | 300 psi                  |
| <b>Glass, Borosilicate</b>                                                                    | 200 psi                  |
| <b>Glass, +3M 3901 Primer</b>                                                                 | 250 psi                  |
| <b>Polycarbonate</b>                                                                          | 400 psi                  |
| <b>Acrylic</b>                                                                                | 250 psi                  |
| <b>Fiberglass</b>                                                                             | 1400 psi                 |
| <b>ABS</b>                                                                                    | 300 psi                  |
| <b>PVC</b>                                                                                    | 520 psi                  |
| <b>Polypropylene</b>                                                                          | 80 psi                   |

|                                                                                                  |          |
|--------------------------------------------------------------------------------------------------|----------|
| <b>Rate of Strength Buildup</b><br>(OLS on Etched Aluminum) <sup>12</sup><br>Bonds tested after: |          |
| <b>1 hr @ RT</b>                                                                                 | 250 psi  |
| <b>6 hrs @ RT</b>                                                                                | 500 psi  |
| <b>24 hrs @ RT</b>                                                                               | 1000 psi |
| <b>7 days @ RT</b>                                                                               | 2000 psi |
| <b>1 mo @ RT</b>                                                                                 | 2000 psi |

|                                                                                             |          |
|---------------------------------------------------------------------------------------------|----------|
| <b>Environmental Aging</b><br>(OLS on Etched Aluminum) <sup>12</sup><br>Bonds tested after: |          |
| <b>24 hrs RT + 2 hrs @ 160°F (71°C)</b>                                                     | 2000 psi |
| <b>24 hrs RT + 2 hrs @ 240°F (116°C)</b>                                                    | 2200 psi |
| <b>1 wk RT + 1 wk @ 90°F/90% RH</b>                                                         | 1800 psi |
| <b>1 wk RT + 1 wk 248°F (120°C)</b>                                                         | 3000 psi |
| <b>1 wk RT + 1 wk H<sub>2</sub>O Immersion</b>                                              | 2000 psi |

# 3M™ Scotch-Weld™

## Epoxy Adhesives

### DP-105 Clear

#### Typical Adhesive Performance Characteristics (continued)

##### Footnotes:

12. Overlap shear (OLS) strengths were measured on 1" wide 1/2" overlap specimens. These bonds were made individually using 1" x 4" pieces of substrate. The thickness of the bond line was 0.005-0.008". All strengths were measured at 70°F (21°C) except where noted. (Test per ASTM D 1002-72.)

The separation rate of the testing jaws was 0.1" per minute for metals, 2" per minute for plastics and 20" per minute for rubbers. The thickness of the substrates were: steel, 0.060"; other metals, 0.05-0.064"; rubber, 0.125"; plastics, 0.125".

13. T-peel strengths were measured on 1" wide bonds at 73°F (23°C). The testing jaw separation rate was 20 inches per minute. The substrates were 0.020" thick. (Tests per ASTM D 1876-61T).

14. Solvent resistance was determined using cured (24 hrs RT + 2hrs 160°F [71°C]) samples (1/2" x 4" x 1/8" thickness) immersed in the test solvent for 1 hour and 1 month. After the allotted period of time the sample was removed and visually examined for surface attack as compared to the control.

Key: A - Unaffected - no change to color or surface texture.  
B - Slight attack - noticeable swelling of surface.  
C - Moderate/severe attack - extreme swelling of surface.

15. Exotherm determined using the stated mass mixed for 1 minute and then by electronic thermocouple measuring the peak temperature and time to that temperature.

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

|                                                                                                                                  | Scotch-Weld DP-105 Clear |
|----------------------------------------------------------------------------------------------------------------------------------|--------------------------|
| <b>Overlap Shear Strength vs Temperature<sup>12</sup></b><br>(Bonds cured 24 hr @ RT + 2 hrs @ 160°F [71°C])<br>Bonds tested at: |                          |
| <b>-67°F (-53°C)</b>                                                                                                             | 3500 psi                 |
| <b>70°F (21°C)</b>                                                                                                               | 2000 psi                 |
| <b>120°F (49°C)</b>                                                                                                              | 400 psi                  |
| <b>150°F (66°C)</b>                                                                                                              | 250 psi                  |
| <b>180°F (82°C)</b>                                                                                                              | 150 psi                  |

|                                                                                                                              |          |
|------------------------------------------------------------------------------------------------------------------------------|----------|
| <b>180° Peel Strength vs Temperature<sup>13</sup></b><br>(Bonds cured 24 hr @ RT + 2 hrs @ 160°F [71°C])<br>Bonds tested at: |          |
| <b>-67°F (-53°C)</b>                                                                                                         | 3.0 piw  |
| <b>70°F (21°C)</b>                                                                                                           | 35.0 piw |
| <b>120°F (49°C)</b>                                                                                                          | 5.0 piw  |
| <b>150°F (66°C)</b>                                                                                                          | 2.0 piw  |
| <b>180°F (82°C)</b>                                                                                                          | 1.0 piw  |

| <b>Solvent Resistance<sup>14</sup></b>                             | One Hour/One Month |
|--------------------------------------------------------------------|--------------------|
| <b>Acetone</b>                                                     | A/A                |
| <b>Isopropyl Alcohol</b>                                           | A/A                |
| <b>Freon TF</b>                                                    | A/A                |
| <b>Freon TMC</b>                                                   | A/B                |
| <b>1,1,1 Trichloroethane</b>                                       | A/A                |
| <b>RMA Flux</b>                                                    | A/A                |
| Key: A - Unaffected, B - Slight Attack, C - Moderate/Severe Attack |                    |

| <b>Exotherm<sup>15</sup></b> | Max. Temp/Time to Reach |
|------------------------------|-------------------------|
| <b>2 gram mass</b>           | 98°F (37°C)/5 min.      |
| <b>20 gram mass</b>          | 230°F (110°C)/3 min.    |

# 3M™ Scotch-Weld™

## Epoxy Adhesives

DP-105 Clear

---

### Handling/Curing Information

### Directions for Use

1. For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental aging resistance desired by user. For specific surface preparations on common substrates, see the following section on Surface Preparation.
2. Uses gloves to minimize skin contact. **Do not** use solvents for cleaning hands.
3. Mixing

#### For Duo-Pak Cartridges

3M™ Scotch-Weld™ Epoxy Adhesive DP-105 Clear is supplied in a dual syringe plastic Duo-Pak cartridge as part of the 3M™ Scotch-Weld™ EPX™ Applicator system. To use, simply insert the Duo-Pak cartridge into the EPX applicator and start the plunger into the cylinders using light pressure on the trigger. Next, remove the Duo-Pak cartridge cap and expel a small amount of adhesive to be sure both sides of the Duo-Pak cartridge are flowing evenly and freely. If automatic mixing of Part A and Part B is desired, attach the EPX mixing nozzle to the Duo-Pak cartridge and begin dispensing the adhesives. For hand mixing, expel the desired amount of adhesive and mix thoroughly. Mix approximately 15 seconds after uniform color is obtained.

#### For Bulk Containers

Mix thoroughly by weight or volume in the proportions specified in the Typical Uncured Properties section. Mix approximately 15 seconds after uniform color is obtained.

4. For maximum bond strength apply adhesive evenly to both surfaces to be joined.
5. Application to the substrates should be made within 3 minutes. Larger quantities and/or higher temperatures will reduce this working time.
6. Join the adhesive coated surfaces and allow to cure at 60°F (16°C) or above until completely firm. Heat up to 200°F (93°C), will speed curing. These products will cure in 48 hours @ 75°F (24°C).
7. Keep parts from moving during cure. Contact pressure is necessary. Maximum shear strength is obtained with a 3-5 mil bond line.
8. Excess uncured adhesive can be cleaned up with ketone type solvents.\*

**Adhesive Coverage:** A 0.005 in. thick bondline will yield a coverage of 320 sq. ft./gallon.

**\*Note:** When using solvents, extinguish all ignition sources and follow the manufacturer's precautions and directions for use.

# 3M™ Scotch-Weld™

## Epoxy Adhesives

### DP-105 Clear

---

#### Surface Preparation

For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental aging resistance desired by the user.

The following cleaning methods are suggested for common surfaces:

##### Steel:

1. Wipe free of dust with oil-free solvent such as acetone, isopropyl or alcohol solvents.\*
2. Sandblast or abrade using clean fine grit abrasives.
3. Wipe again with solvent to remove loose particles.
4. If a primer is used, it should be applied within 4 hours after surface preparation.

##### Aluminum:

1. Vapor Degrease: Perchlorethylene condensing vapors for 5-10 minutes.
2. Alkaline Degrease: Oakite 164 solution (9-11 oz./gallon water) at 190°F ± 10°F (88°C ± 5°C) for 10-20 minutes. Rinse immediately in large quantities of cold running water.
3. Acid Etch: Place panels in the following solution for 10 minutes at 150°F ± 5°F (66°C ± 2°C).

|                                |                        |
|--------------------------------|------------------------|
| Sodium Dichromate              | 4.1 - 4.9 oz./gallon   |
| Sulfuric Acid, 66°Be           | 38.5 - 41.5 oz./gallon |
| 2024-T3 aluminum (dissolved)   | 0.2 oz./gallon minimum |
| Tap Water as needed to balance |                        |
4. Rinse: Rinse panels in clean running tap water.
5. Dry: Air dry 15 minutes; force dry 10 minutes at 150°F ± 10°F (66°C ± 5°C).
6. If primer is to be used, it should be applied within 4 hours after surface preparation.

##### Plastics/Rubber:

1. Wipe with isopropyl alcohol.\*
2. Abrade using fine grit abrasives.
3. Wipe with isopropyl alcohol.\*

##### Glass:

1. Solvent wipe surface using acetone or MEK.\*
2. Apply a thin coating (0.0001 in. or less) of primer such as 3M™ Scotch-Weld™ Primer EC-3901 to the glass surfaces to be bonded and allow the primer to dry before bonding.

**\*Note:** When using solvents, extinguish all ignition sources and follow the manufacturer's precautions and directions for use.

# 3M™ Scotch-Weld™

## Epoxy Adhesives

DP-105 Clear

---

### Surface Preparation (continued)

- For small or intermittent applications the 3M™ Scotch-Weld™ EPX™ Applicator is a convenient method of application.
- For larger applications, these products may be applied by use of flow equipment.
- Two part meter/mixing/dispensing equipment is available for intermittent or production line use. These systems may be desirable because of their variable shot size and flow rate characteristics and are adaptable to many applications.

---

### Storage and Shelf Life

Store 3M™ Scotch-Weld™ Epoxy Adhesive DP-105 Clear at 60-80°F (15-27°C) for maximum shelf life. These epoxy adhesive products have a shelf life of 2 years in their unopened containers and 15 months in Duo-Pak containers.

# 3M™ Scotch-Weld™

## Epoxy Adhesives

### DP-105 Clear

---

#### Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

---

#### Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

---

#### Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

---

#### Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

---

#### Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

---

ISO 9001:2000

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.



#### Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
800-362-3550 • 877-369-2923 (Fax)  
www.3M.com/industrial



*Recycled Paper*  
40% pre-consumer  
10% post-consumer

3M, Scotch-Weld and EPX are trademarks of 3M Company.  
Printed in U.S.A.  
©3M 2009 78-6900-9675-1 (12/09)